

TECHNICAL DATA SHEET

327 HOT N COLD

Solvent Cement for PVC Plastic Pipe

GENERAL DESCRIPTION: 327 Hot N Cold is a clear, medium bodied, very fast setting, high strength PVC solvent cement for all classes and schedules of pipe and fittings with interference fit through 6 inch diameter, Schedule 80 through 4 inch diameter. Can be used without primer on non-pressure systems if local codes permit.

APPLICATION: 327 Hot N Cold is specially formulated for use in a wide range of temperatures encountered during all seasons of the year. Successful, high strength joints can be made at temperatures as low as -15°F (-26°C) and as high as 110°F (43°C). It is suitable for use on rigid and flexible PVC pipe and fittings and can be used in very wet condition and/or where quick pressurization of the piping systems is desired. Meets ASTM D 2546 Standards

Detailed directions on making solvent cemented joints are printed on the container label. An installation DVD/CD covering solvent cementing is available. It not only describes the basic principles of solvent cementing, but also covers the handling, storage and use of our products. It is highly recommended that the installer review the instructions supplied by the pipe and fitting manufacturer. **NOTE:** HP International solvent cements must never be used in a PVC system using or being tested by compressed air or gases; including air-over-water booster.

AVAILABILITY: This product is available in ¼ pint (118 ml), ½ pint (237 ml), pint (473 ml), quart (946 ml) and gallon (3.785 l) metal can

SPECIFICATIONS:

COLOR:	Clear
RESIN:	PVC
SPECIFIC GRAVITY:	0.935 ± 0.04
BROOKFIELD VISCOSITY:	Minimum 500 cP @ 73° ± 2°F (23° ± 1°C)

SHELF LIFE: 3 years in tightly sealed containers. The date code of manufacture is stamped on the bottom of the container. Stability of the product is limited by the evaporation of the solvent when the container is opened. Evaporation of solvent will cause the cement to thicken and reduce its effectiveness. Adding of thinners to change viscosity is not recommended and may significantly change the properties of the cement.

QUALITY ASSURANCE: 327 Hot N Cold is carefully evaluated to assure that consistent high quality is maintained. Fourier transforms infrared spectroscopy, gas chromatography, and additional in depth testing ensures each batch is manufactured to exacting standards. A batch identification code is stamped on each can and assures traceability of all materials and processes used in manufacturing this solvent cement.

SHIPPING:

For One Liter and Above

Proper Shipping Name: Adhesive
Hazard Class: 3
Identification Number: UN 1133
Packing Group: II
Label Required: Flammable Liquid

For Less than One Liter

Proper Shipping Name: Consumer Commodity
Hazard Class: ORM-D

SAFETY AND ENVIRONMENTAL PRECAUTIONS: This product is flammable and considered a hazardous material. In conformance with the Federal Hazardous Substances Labeling Act, the following hazards and precautions are given. Purchasers who repackage this product must also conform to all local, state and federal labeling, safety and other regulations. VOC emissions do not exceed 510 grams per liter.



+91-22-28324739



sales@hpint.in



<http://hpgroups.in>



HP International
11, Unique House, Chakala Rd,
Andheri (East), Mumbai - 400 099.

TECHNICAL DATA SHEET

327 HOT N COLD

Solvent Cement for PVC Plastic Pipe

**DANGER: EXTREMELY FLAMMABLE. VAPOR HARMFUL.
MAY BE HARMFUL IF SWALLOWED. MAY IRRITATE SKIN OR EYES.**

Keep out of reach of children. Do not take internally. Keep away from heat, spark, open flame and other sources of ignition. Vapors may ignite explosively. Solvent cement vapors are heavier than air and may travel to source(s) of ignition at or near ground or lower level(s) and flash back. Keep container closed when not in use. Store between 40°F (5°C) and 110°F (44°C). Avoid breathing of vapors. Use only in well-ventilated area. If confined or partially enclosed, use forced ventilation. When necessary, use local exhaust ventilation to remove harmful airborne contaminants from employee breathing zone and to keep contaminants below 25 ppm TWA. Atmospheric levels must be maintained below established exposure limits contained in Section II of the Material Safety Data Sheet (MSDS). If airborne concentrations exceed those limits, use of a NIOSH approved organic vapor cartridge respirator with full face-piece is recommended. The effectiveness of an air-purifying respirator is limited. Use it only for a single short-term exposure. For emergency and other conditions where short-term exposure guidelines may be exceeded, use an approved positive pressure self-contained breathing apparatus. Do not smoke, eat or drink while working with this product. Avoid contact with skin, eyes and clothing. May cause eye injury. Protective equipment such as gloves, goggles and impervious apron should be used. Carefully read Material Safety Data Sheet and follow all precautions. Do not use this product for other than intended use. "SARA Title III Section 313 Supplier Notification": This product contains toxic chemicals subject to the reporting requirements of Section 313 of the Emergency Planning and Community Right-to-Know Act (EPCRA) of 1986 and of 40CFR372. This information must be included in all MSDS that are copied and distributed for this material.

FIRST AID:

Inhalation: If overcome with vapors, remove to fresh air. If not breathing, give artificial respiration. If breathing is difficult, give oxygen. Call physician.

Eye Contact: Flush with plenty of water for 15 minutes and call a physician.

Skin Contact: Wash skin with plenty of soap and water for at least 15 minutes. If irritation develops, get medical attention.

Ingestion: If swallowed, give 1 or 2 glasses of water or milk. Do not induce vomiting. Contact physician or poison control center immediately.

SPECIAL PRECAUTION: Do not use a dry granular calcium hypochlorite as a disinfecting material for water purification in potable water piping systems. The introduction of granules or pellets of calcium hypochlorite with PVC and CPVC solvent cements and primers (including their vapors) may result in a violent chemical reaction if a water solution is not used. It is advisable to purify lines by pumping chlorinated water into the piping system – this solution will be nonvolatile. Furthermore, dry granular calcium hypochlorite should not be stored or used near solvent cements and primers.

IMPORTANT NOTE: This product is intended for use by skilled individuals at their own risk. These suggestions and data are based on information we believe to be reliable. Installers should verify for themselves that they can make satisfactory joints under varying conditions. Toward this end, it is highly desirable that they receive personal instruction from trained instructors or competent, experienced installers. Contact HP International or your supplier for additional information or instructions.

WARRANTY: HP International warrants that all new HP International products shall be of good quality and free from defects in material and workmanship for the shelf life as indicated on the product. If any HP International product becomes defective, or fails to conform to our written limited warranty under normal use and storage conditions, then HP International will, without charge, replace the nonconforming product. However, this limited warranty shall not extend to, nor shall HP International be responsible for, damages or loss resulting from accident, misuse, negligent use, improper application, or incorporation of HP International products into other products. In addition, any repackaging of HP International products also shall void the limited warranty. HP International shall not be responsible for, nor does this limited warranty extend to, consequential damage, or incidental damage or expense, including without limitation, injury to persons or property or loss of use. Please refer to our standard HP International Limited Warranty for additional provisions.



+91-22-28324739



sales@hpint.in



<http://hpgroups.in>



HP International
11, Unique House, Chakala Rd,
Andheri (East), Mumbai - 400 099.